

WHAT IS CLAIMED IS:

1. A non-aqueous electrochemical apparatus where the difference ($\gamma_l - \gamma_{se}$) between the surface tension γ_l of electrolyte and the surface free energy γ_{se} of electrode is not more than 10 dynes/cm.
2. A non-aqueous electrochemical apparatus where the difference ($\gamma_l - \gamma_{ss}$) between the surface tension γ_l of electrolyte and the surface free energy γ_{ss} of separator interposed between electrodes is not more than 10 dynes/cm.
3. A non-aqueous electrochemical apparatus where the difference ($\gamma_l - \gamma_{se}$) between the surface tension γ_l of electrolyte and the surface free energy γ_{se} of electrode is not more than 10 dynes/cm and the difference ($\gamma_l - \gamma_{ss}$) between the surface tension γ_l of electrolyte and the surface free energy γ_{ss} of separator is not more than 10 dynes/cm.
4. A non-aqueous electrochemical apparatus according to any one of claims 1-3, wherein the surface tension γ_l of electrolyte is 10-45 dynes/cm.
5. A non-aqueous electrochemical apparatus comprising solid elements having a surface free energy of 1-35 dynes/cm where the surface tension of electrolyte is 10-45 dynes/cm.
6. A non-aqueous electrochemical apparatus according to claim 5, wherein the solid elements are electrodes containing a carbon material.
7. A non-aqueous electrochemical apparatus

according to claim 6, wherein the non-aqueous electrolyte contains a surface active agent.

8. A non-aqueous electrochemical apparatus according to claim 7, wherein the surface active agent is a fluorine-containing surface active agent.

9. A non-aqueous electrochemical apparatus according to claim 8, wherein the fluorine-containing surface active agent comprises at least one compound selected from the group consisting of fluoroalkyl(C2-C20)carboxylic acids, disodium N-perfluorooctanesulfonylglutamate, sodium 3-[fluoroalkyl(C6-C11)oxy]-1-alkyl(C3-C4)sulfonate, sodium 3-[ω -fluoroalkanoyl(C6-C8)-N-ethylamino]-1-propanesulfonate, N-[3-(perfluorooctanesulfonamide)propyl]-N,N-dimethyl-N-carboxymethylene ammonium betaine, perfluoroalkylcarboxylic acids (C7-C13), perfluorooctanesulfonic acid diethanolamide, perfluoroalkyl(C4-C12)sulfonates (Li, Na, K), N-propyl-N-(2-hydroxyethyl)perfluorooctanesulfonamide, perfluoroalkyl(C6-C10)sulfonamidopropyltrimethylammonium salts, perfluoroalkyl(C6-C10)-N-ethylsulfonylglycine salts (K), bis(N-perfluorooctylsulfonyl-N-ethylaminoethyl) phosphate, monoperfluoroalkyl(C6-C16)ethylphosphoric acid esters, and perfluoroalkylethylene oxide adducts.

10. A non-aqueous electrochemical apparatus according to claim 9, wherein the fluorine-containing surface active agent is shown by the formula (1):

$C_nF_{2n+1}SO_2N(C_mH_{2m+1})CH_2CH_2O(CH_2CH_2O)_lH$ in which n is 4-18, m

is 1-4, and l is 5-25.

11. A non-aqueous electrochemical apparatus according to claim 9, wherein the fluorine-containing surface active agent is shown by the formula (2):
$$C_nF_{2n+1}-X-(CH_2-CH_2-O)_m-Y$$
 in which -X- is -CONH- or -SO₂NR- (R is an alkyl group of 1-8 carbon atoms), -Y is -H, -OH, -CH₃, -PO₃W₂ or -SO₃W (W is an alkali metal), n is 3-10, and m is 2-100.



12. A non-aqueous electrochemical apparatus according to claim 7, wherein the solid elements comprise a negative electrode containing a carbon material and a positive electrode containing a lithium-containing metal oxide, and the non-aqueous electrolyte contains a non-aqueous solvent, a solute and a fluorine-containing surface active agent, said non-aqueous solvent comprising at least one compound selected from the group consisting of ethylene carbonate, propylene carbonate, ethylmethyl carbonate, diethyl carbonate, dimethyl carbonate, γ -butyrolactone, γ -valerolactone, α -acetyl- γ -butyrolactone, α -methyl- γ -butyrolactone, methyl acetate, ethyl acetate, methyl propionate, ethyl butyrate, butyl acetate, n-propyl acetate, isobutyl propionate and benzyl acetate.

13. A non-aqueous electrochemical apparatus according to claim 12, wherein 80% by volume or more of the non-aqueous solvent comprises at least one non-aqueous solvent selected from the group consisting of propylene carbonate and γ -butyrolactone.

14. A non-aqueous electrochemical apparatus according to claim 7, wherein the non-aqueous electrolyte additionally contains a carbonic acid ester additive or a sulfur compound additive.
15. A non-aqueous electrochemical apparatus according to claim 7, wherein the non-aqueous electrolyte contains a non-aqueous solvent, a solute and a surface active agent, and the non-aqueous solvent contains a plurality of cyclic compounds and the solute is a compound containing lithium as a cation component.
16. A non-aqueous electrochemical apparatus according to claim 15, wherein the cyclic compound is a mixture of at least two compounds selected from the group consisting of cyclic esters, cyclic ethers, cyclic acid anhydrides and derivatives of these compounds.
17. A non-aqueous electrochemical apparatus according to claim 15, wherein the surface active agent is a fluorine-containing surface active agent.
18. A non-aqueous electrochemical apparatus according to claim 16, wherein at least one of a plurality of the cyclic compounds has a melting point of not higher than -20°C .
19. A non-aqueous electrochemical apparatus according to claim 16, wherein the cyclic ester is selected from the group consisting of cyclic carbonic acid esters, cyclic carboxylic acid esters, cyclic phosphoric acid esters, cyclic phosphorous acid esters,

cyclic boric acid esters, cyclic sulfurous acid esters, cyclic sulfuric acid esters, cyclic nitrous acid esters, cyclic nitric acid esters, and cyclic silicic acid esters.

20. A non-aqueous electrochemical apparatus according to claim 15, wherein the solute contains at least one compound selected from the group consisting of lithium hexafluorophosphate (LiPF_6) and lithium tetrafluoroborate (LiBF_4) and at least one compound selected from the group consisting of lithium bistrifluoromethanesulfonimide ($(\text{CF}_3\text{SO}_2)_2\text{NLi}$) having the following structural formula (3) and lithium bispentafluoroethanesulfonimide ($(\text{C}_2\text{F}_5\text{SO}_2)_2\text{NLi}$) having the following structural formula (4):



21. A non-aqueous electrochemical apparatus according to claim 14, wherein the carbonic acid ester additive comprises at least one compound selected from the group consisting of vinylene carbonate,

phenylethylene carbonate, phenylvinylene carbonate, diphenylvinylene carbonate, trifluoropropylene carbonate, chloroethylene carbonate, methoxypropylene carbonate, vinylethylene carbonate, catechol carbonate, tetrahydrofuran carbonate, diphenyl carbonate, and diethyl dicarbonate.

22. A non-aqueous electrochemical apparatus according to claim 14, wherein the sulfur compound additive comprises at least one compound selected from the group consisting of ethylene sulfite, ethylene trithiocarbonate, vinylene trithiocarbonate, catechol sulfite, tetrahydrofuran sulfite, sulfolane, 3-methylsulfolane, sulfolene, propanesultone, and 1,4-butanedisultone.